

Zinc Oxide

Model: MX-50

Analysis Mode:

Standard mode

(Accuracy: HI)

Weight 5g

Temperature 200C


Analysis Time 2.1min

Moisture Content

Mean Value 0.148%

Repeatability 0.0084%

CV Value 5.68%



Remarks:

Average Moisture Content

0.080%

Repeatability

0.0099%

Average Process Time

19.0min

At 200C with 2g by
Karl Fischer method.